



Black Acoustical Insulation

Black Acoustical Insulation

Wall and Ceiling Liner M

Description

Knauf Wall and Ceiling Liner M is a black flexible fiber glass blanket with a black mat facing adhered to one surface. It provides thermal and acoustical insulation and a visual barrier. Its smooth, tough surface resists damage during installation.

Application

Knauf Wall and Ceiling Liner M is designed for use as an acoustical and visual barrier for walls and ceilings where a black surface is required. It is primarily used in theaters, sound studios, public concourses and other areas where acoustical treatment is needed. It is intended to be mechanically fastened to walls and covered with fabric or draping, or suspended above linear metal and metal pan ceiling systems to serve as both a visual and acoustical treatment.

Features and Benefits

Acoustical Barrier

- Reduces airborne sound.
- Significantly improves STC ratings of wall configurations.

Technical Data

Surface Burning Characteristics

(UL/ULC Listed)

- Does not exceed 25 Flame Spread, 50 Smoke Developed when tested in accordance with ASTM E 84, CAN/ULC S102-M88, NFPA 255 and UL 723.

Service Temperature (ASTM C 411)

- Maximum 250°F (121°C).

Microbial Growth

(ASTM C 1338, G 21, G 22)

- Does not support microbial growth.

Water Vapor Sorption (ASTM C 1104)

- Less than 3% by weight.

Air Velocity (ASTM C 1071))

- Maximum 6000 fpm (1829 mpm).

Packaging

- Knauf Wall and Ceiling Liner M is packaged in a strong, white poly sleeve that offers excellent protection from abuse, dust and moisture.

Black Acoustical Board

Description

Knauf Black Acoustical Board is a heavy density fiber glass board insulation made from inorganic glass fibers bonded by a thermosetting resin. The base board is amber with a black polymer top layer of fiber glass, and a black overspray applied to provide a smooth, tough finish.

Application

Knauf Black Acoustical Board is designed for use as acoustical insulation and/or a visual barrier on walls and ceilings, where system design requires a rigid product and where additional strength and abuse resistance are required. The black surface provides a visual barrier with an aesthetic appearance, in both wall and ceiling applications. The product is typically used where framing members are not present.

Features and Benefits

Acoustical Barrier

- Reduces airborne sound transmission.
- Significantly improves STC ratings of wall configurations.

Technical Data

Surface Burning Characteristics

(UL/ULC Listed)

- Does not exceed 25 Flame Spread, 50 Smoke Developed when tested in accordance with ASTM E 84, CAN/ULC S102-M88, NFPA 255 and UL 723.

Service Temperature (ASTM C 411)

- Maximum 250°F (121°C).

Microbial Growth

(ASTM C 1338, G 21, G 22)

- Does not support microbial growth.

Water Vapor Sorption (ASTM C 1104)

- Less than 3% by weight.

Air Velocity (ASTM C 1071))

- Maximum 4000 fpm (1219 mpm).

Packaging

- Knauf Black Acoustical Board is packaged in cartons that offer excellent protection from abuse, dust and moisture.
- Cartons are unitized for easy handling and storage.

**Wall and Ceiling Liner M Noise Reduction Coefficients
(ASTM C 423, Type A Mounting)**

| Density | Thickness | NRC |
|------------------------------------|-------------|-----|
| 1.0 PCF (16 kg/m ³) | 1" (25 mm) | .60 |
| | 1½" (38 mm) | .80 |
| | 2" (51 mm) | .85 |
| 1.5 PCF (24 kg/m ³) | ½" (13 mm) | .50 |
| | 1" (25 mm) | .70 |
| | 1½" (38 mm) | .80 |
| 2.0 PCF (32 kg/m ³) | 2" (51 mm) | .90 |
| | ½" (13 mm) | .45 |
| | 1" (25 mm) | .70 |

**Black Acoustical Board Sound Absorption Coefficients
(ASTM C 423, Type A Mounting)**

| Density | Thickness | 1/3 Octave Band Center Frequency (cycles/sec.) | | | | | | NRC |
|-------------------------------------|-------------|--|-----|------|------|------|------|-----|
| | | 125 | 250 | 500 | 1000 | 2000 | 4000 | |
| 2.25 PCF (36 kg/m ³) | 2" (25 mm) | .26 | .62 | 1.05 | 1.07 | 1.04 | 1.05 | .95 |
| 3.0 PCF (48 kg/m ³) | 1" (51 mm) | .13 | .24 | .56 | .83 | .92 | .98 | .65 |
| | 1½" (76 mm) | .19 | .41 | .89 | 1.02 | 1.03 | 1.04 | .85 |
| | 2" (25 mm) | .33 | .67 | 1.07 | 1.07 | 1.03 | 1.06 | .95 |

Wall and Ceiling Liner M Forms Available

| Density | Thickness | R-Value | Width | Length |
|------------------------------------|-------------|---------|------------------|----------------|
| 1.0 PCF (16 kg/m ³) | 1" (25 mm) | 3.6 | 48" (1219 mm) | 100' (30.48 m) |
| | 1½" (38 mm) | 5.4 | | 50' (15.24 m) |
| | 2" (51 mm) | 7.1 | | 50' (15.24 m) |
| 1.5 PCF (24 kg/m ³) | ½" (13 mm) | 2.0 | | 100' (30.48 m) |
| | 1" (25 mm) | 4.2 | | 100' (30.48 m) |
| | 1½" (38 mm) | 6.0 | | 50' (15.24 m) |
| 2.0 PCF (32 kg/m ³) | 2" (51 mm) | 8.0 | | 50' (15.24 m) |
| | ½" (13 mm) | 2.1 | | 100' (30.48 m) |
| | 1" (25 mm) | 4.2 | | 50' (15.24 m) |



- Excellent acoustical as well as thermal insulation to walls and ceilings.



- Knauf Wall and Ceiling Liner M is primarily used in theatres, sound studios and public concourses.



- Knauf Black Acoustical Board is used as acoustical insulation and/or visual barrier, where system design requires a rigid product.

For more information call (800) 825-4434, ext. 8300

or visit us online at www.KnaufInsulation.com



Knauf Insulation GmbH
One Knauf Drive
Shelbyville, IN 46176

Sales and Marketing (800) 825-4434, ext. 8300

Technical Support (800) 825-4434, ext. 8212

Customer Service (866) 445-2365

Fax (317) 398-3675

World Wide Web www.KnaufInsulation.com

©2006 Knauf Insulation GmbH.

Black Acoustical Board Forms Available

| Density | Thickness | R-Value | Width | Length |
|-------------------------------------|-------------|---------|-----------------|---------------|
| 2.25 PCF (36 kg/m ³) | 1" (25 mm) | 4.3 | 24" (610 mm) | 48" (1219 mm) |
| | 1½" (38 mm) | 6.5 | | 48" (1219 mm) |
| | 2" (51 mm) | 8.6 | | 48" (1219 mm) |
| 3.0 PCF (48 kg/m ³) | 2" (51 mm) | 8.6 | | 48" (1219 mm) |

Fiber Glass and Mold

Fiber glass insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated with organic materials. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced.

Notes

The chemical and physical properties of Knauf Black Acoustical Insulation represent typical average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Check with your Knauf sales representative to assure information is current.



LEED Eligible Product

Use of this product may help building projects meet green building standards as set by the Leadership in Energy and Environmental Design (LEED) Green Building Rating System.
Credit 4.1 - 4.2 Recycled Content
Credit 5.1 - 5.2 Regional Materials