

Jet Stream® Ultra Blowing Wool Insulation

Submittal Date _____



APPLICATION

Knauf Insulation Jet Stream ULTRA Glass Mineral Wool Blowing Insulation is installed in open attics of both new and existing structures and/or in closed cavity applications with the BIBS system (Blow-in-Blanket System). Jet Stream ULTRA, when used in closed cavity applications is BIBS approved and can only be installed by BIBS certified installers to ensure the highest quality installed performance. Jet Stream ULTRA is an excellent product for Blow-in-Blanket applications. It will dense-pack in wall cavities with no settling.

PRODUCT FEATURES

Excellent Thermal Performance

- Fills all gaps and voids, creating a thermal barrier against outside air and better temperature control, reducing fuel usage and utility bills
- Resists heat flow with an R-value of
 - R-15 in 2 x 4 construction
 - R-23 in 2 x 6 construction

Convenient

- One product, one inventory, two applications.

Energy Conservation

- Reduces fuel usage and utility bills for heating and air conditioning.

Sustainable

- Has a high degree of recycled content.

Noise Reduction

- Improves Sound Transmission Class (STC) ratings by 4 to 10 points.

Installation

- Blows fast and smooth.

Permanence

- Non-combustible, non-corrosive.
- Will not rot, mildew or deteriorate

THERMAL PERFORMANCE

Jet Stream ULTRA Blowing Insulation provides you with a choice of R-values based on the installed thickness and installed weight per square foot. The tables to the right show the minimum requirements for obtaining the desired R-value.

The stated thermal resistance (R-value) is provided by installing the required number of bags per 1,000 ft² of net area, at not less than the labeled minimum thickness (per the manufacturer's instructions). Failure to install both the required number of bags and at least the minimum thickness will result in lower insulation R-values.

Field blending of this product with other loose fill insulation or application of this product in conjunction with adhesive or binder systems may affect its thermal performance and is not recommended by the manufacturer.

Framing Adjustments

As shown in the table on the last page, to compensate for the framing members in open attic applications, the number of bags per 1,000 ft² of area.

SPECIFICATION COMPLIANCE

- ASTM C764; Type I
- HH-1030B; Class B

INDOOR AIR QUALITY

- UL Environment
 - GREENGUARD certified
 - GREENGUARD Gold certified
 - Validated to be formaldehyde-free.

Knauf Insulation Jet Stream ULTRA Glass Mineral Wool Blowing Insulation is manufactured with a high degree of recycled content and UL Environment verification every 6 months.

EQUIPMENT REQUIRED

To achieve labeled R-value, this product must be applied with a pneumatic blowing machine and a corrugated hose with a minimum ¼" internal corrugation, a minimum length of 150' and a diameter of at least 3". Coils in the hose should not be less than 36" in diameter. Acceptable material feed rate is 5–35 lbs./minute. The recommended feed rate is 15–25 lbs./minute. For closed cavity applications, netting must be applied.

PACKAGING

Jet Stream ULTRA Blowing Insulation is packaged in a strong, white poly bag that offers excellent protection from abuse, dust and moisture. Knauf Insulation packages are lightweight, stack without slipping and are easy to handle and store.

GLASS MINERAL WOOL AND MOLD

Glass mineral wool insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold, it must be discarded. If the material is wet, but shows no evidence of mold, it should be dried rapidly and thoroughly.

NOTES

The chemical and physical properties of Knauf Insulation Jet Stream **ULTRA** Blowing Insulation represent typical average values determined in accordance with accepted test methods. The data is supplied as technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Check with your Knauf Insulation Territory Manager to ensure information is current.

Technical Data

Property (Unit)	Test	Performance
Corrosion	ASTM C764	Pass
Combustibility	ASTM E136	Non-combustible
Water Vapor Sorption (by weight)	ASTM C1104	Less than 5%
Critical Radiant Flux	ASTM E970	Greater than 0.12 W/cm ²
Mold Growth	ASTM C1338	Pass
Surface Burning Characteristics (flame spread/smoke developed)	ASTM E84, CAN 4-S102.2	25/50

Jet Stream® Ultra Blowing Wool Insulation

Submittal Sheet



Open Attic Application					
R-Value*	Bags/1,000 ft ²	Maximum Coverage	Minimum Weight	Initial Installed Thickness	Minimum Settled Thickness**
To obtain an insulation resistance (R-value) of:	The number of bags/1,000 ft ² of net area should not be less than:	Contents of this bag should not cover more than:	The weight/ft ² of installed insulation should not be less than:	Installed insulation should not be less than:	Installed insulation should not be less than:
R-60	29.7	33.6 ft ²	0.952 lbs.	19.750"	19.750"
R-49	23.5	42.5 ft ²	0.753 lbs.	16.375"	16.375"
R-44	20.9	47.8 ft ²	0.670 lbs.	14.875"	14.875"
R-38	17.8	56.2 ft ²	0.569 lbs.	13.000"	13.000"
R-30	13.6	73.3 ft ²	0.437 lbs.	10.375"	10.375"
R-26	11.8	85.0 ft ²	0.377 lbs.	9.125"	9.125"
R-22	9.8	102.2 ft ²	0.313 lbs.	7.750"	7.750"
R-19	8.4	119.3 ft ²	0.268 lbs.	6.750"	6.750"
R-13	5.7	175.3 ft ²	0.183 lbs.	4.750"	4.750"
R-11	4.7	210.8 ft ²	0.152 lbs.	4.000"	4.000"

Bag Net Weight - Nominal 32 lbs., Minimum 31 lbs.

Coverage and installation data were determined using a Volu-Matic® II blowing machine in third gear with 13" gate opening, 2.0 psi air pressure, 150' of 3" diameter internally-corrugated hose.

*"R" means resistance to heat flow. The higher the R-value, the greater the insulating power. To get the marked R-value, it is essential that this insulation be installed properly. If you do it yourself, get instructions and follow them carefully. Instructions do not come with this package.

**Based on Third Party 2-year settling study, the predicted settlement over a 20-year period would be 1 percent or less. This amount of settling is thermally insignificant. Therefore, the installed and settled thicknesses are effectively the same.

Volu-Matic® II is a registered trademark of Unisul.

Cavity Wall Application						
Framing	Cavity Depth	R-Value*	Density	Bags/1000 ft ²	Maximum Coverage/Bag	Net Minimum Weight/ft ²
		To obtain an insulation resistance of		The number of bags per 1000 ft ² of net area should not be less than:	Contents of this bag should not cover more than:	The weight per ft ² of installed insulation should not be less than:
2" x 4"	3.50"	R-15	1.8 lb/ft ³	16.4 bags	61.0 ft ²	0.525 lb
2" x 6"	5.50"	R-23	1.8 lb/ft ³	25.8 bags	38.8 ft ²	0.825 lb
2" x 8"	7.25"	R-31	1.8 lb/ft ³	34.0 bags	29.4 ft ²	1.088 lb
2" x 10"	9.25"	R-39	1.8 lb/ft ³	43.4 bags	23.1 ft ²	1.388 lb

Framing Adjustments Open Attic Application						
R-Value	Bags/1,000 ft ²					
	16" O.C. Framing			24" O.C. Framing		
	2" x 4"	2" x 6"	2" x 8"	2" x 4"	2" x 6"	2" x 8"
R-60	29.2	28.9	28.6	29.4	29.1	28.9
R-49	23.0	22.7	22.4	23.2	22.9	22.7
R-44	20.4	20.1	19.8	20.6	20.3	20.1
R-38	17.3	17.0	16.7	17.4	17.2	17.0
R-30	13.2	12.9	12.6	13.3	13.1	12.9
R-26	11.3	11.0	10.8	11.4	11.2	11.0
R-22	9.3	9.1	8.8	9.5	9.3	9.1
R-19	7.9	7.7	7.4	8.1	7.9	7.7
R-13	5.3	5.0	4.8	5.4	5.2	5.0
R-11	4.3	4.1	3.8	4.4	4.3	4.1

This product is covered by one or more U.S. and/or other patents. See patent www.knaufinsulation.us/patents.

